

Share Group Limited

Pingqiao Industrial Park
Tiantai County, Zhejiang Province 317203, CHINA
Phone: 0086-576-8950-8685 | Fax: 0086-576-8543 2410
sales@sharefilters.com | www.sharefilters.com

Chemical Resistance Chart

Fiber Type	Continuous Working Temp.	Max. Working Temp.	Filtration Characteristic	Abrasion Resistance	Hydrolysis Resistance	Acid Resistance	Alkalis Resistance	Oxidation Resistance
PVC	75°C	80°C	Good	Excellent	Excellent	Excellent	Excellent	Good
PP	90°C	100°C	Good	Good	Excellent	Excellent	Excellent	Poor
PA	110°C	115°C	Moderate	Excellent	Poor	Moderate	Good	Moderate
PAN Copolymer	120°C	130°C	Good	Good	Good	Moderate	Moderate	Good
PET	135°C	150°C	Excellent	Excellent	Poor	Moderate	Poor	Good
m-Aramid	180°C	220°C	Excellent	Excellent	Moderate	Moderate	Moderate	Good
PPS	190°C	200°C	Excellent	Good	Excellent	Excellent	Excellent	Moderate
Polyimide	240°C	280°C	Excellent	Moderate	Good	Good	Moderate	Excellent
Polyetrafluoroethylene	250°C	280°C	Moderate	Good	Excellent	Excellent	Excellent	Excellent
Fiberglass	250°C	280°C	Moderate	Moderate	Excellent	Poor	Moderate	Excellent

Remarks:

PVC: Polyvinylchloride
PP: Polypropylene
PA: Polyamide or Nylon
PET: Polyester