

Share Group Limited

Pingqiao Industrial Park
 Tiantai County, Zhejiang Province 317203, CHINA
 Phone: 0086-576-8950-8685 | Fax: 0086-576-8543 2410
 sales@sharefilters.com | www.sharefilters.com

Fabric Number	Mesh count		Thread Diameter	Mesh Opening	Open Area	Fabric Thickness	Weight
No.	cm mesh/inch		micron	micron	%	micron	g/m2
JPP5	5	12	500	1500	56	850	271
JPP6	6	16	400	1267	58	780	208
JPP7	7	18	350	1079	57	675	186
JPP8	8	20	350	900	52	685	212
JPP9	9	24	250	860	60	455	145
JPP10	10	25	300	700	49	576	195
JPP12	12	30	250	583	49	470	162
JPP12	12	35	300	533	41	585	234
JPP14	14	40	300	414	34	595	273
JPP16	16	40	200	425	46	370	139
JPP16	16	50	250	375	36	485	217
JPP20	20	50	150	350	49	375	98
JPP20	20	50	200	300	36	385	173
JPP24	24	60	150	267	41	285	117
JPP28	28	70	120	237	44	215	87
JPP30	30	76	120	213	41	225	94
JPP32	32	80	100	213	46	165	69
JPP36	36	90	100	178	41	178	78
JPP40	40	100	100	150	36	190	87
JPP43	43	110	80	152	43	135	60
JPP48	48	120	80	130	38	145	62
JPP56	56	140	60	120	44	85	44
JPP59	59	150	60	110	42	98	46
JPP64	64	160	60	100	37	105	50
JPP72	72	180	50	90	41	82	39
JPP80	80	200	50	75	36	90	43
JPP100	100	250	40	60	36	65	35
JPP120	120	305	40	43	25	70	29
JPP130	130	330	40	37	23	75	31
JPP140	140	355	30	38	33.7	60	33
JPP150	150	381	30	34	30.25	52	26
JPP165	165	420	30	28	20.7	51	29
JPP180	180	460	30	25	19.5	58	31
JPP200	200	510	30	16	10.2	58	35

Fabric number

The fabric number is composed of:

Mesh-count n **110**-80W PW

(White = W; yellow = Y)

Thread ϕ dnom 110-**80W** PW

Fabric colour 110-80**W** PW

Type of weave 110-80**W PW** (Plain Weave = PW)